Amendments to the Claims

Claims 1-6 (Canceled).

Claim 7 (Currently amended):

A thin film chip resistor resistant to moisture without use of

metallic tantalum comprising:

a substrate;

a <u>single</u> continuous metal thin film resistive layer directly attached to the substrate, the metal thin film layer being non-tantalum;

a non-tantalum chip resistor termination attached on each end of the metal thin film resistive
layer; an outer moisture barrier consisting of tantalum pentoxide directly overlaying and
contacting the metal thin film resistive layer for reducing failures due to electrolytic
corrosion under powered moisture conditions; and

the outer moisture barrier formed from deposition of tantalum oxide on the metal thin film resistive layer and not through oxidation of tantalum.

Claim 8 (Original): The thin film resistor of claim 7 wherein the metal film layer is an alloy containing nickel.

Claim 9 (Original): The thin film resistor of claim 7 wherein the metal film layer is an alloy containing chromium.

Claim 10 (Original): The thin film resistor of claim 7 wherein the metal film layer is a nickel-chromium alloy.

BEST AVAILABLE COPY

Claim 11 (Canceled).

Claim 12 (Original): The thin film resistor of claim 7 wherein the tantalum pentoxide layer is overlaid by sputtering.

Claim 13 (Previously presented): A nickel-chromium alloy thin film chip resistor resistant to moisture without use of metallic tantalum comprising:

an alumina substrate;

a single nickel-chromium alloy thin film layer directly contacting the substrate;

a non-tantalum chip resistor termination attached on each end of the nickel-chromium alloy thin film;

an outer moisture barrier consisting of tantalum pentoxide directly overlaying and contacting the nickel-chromium alloy thin film layer for reducing failures due to electrolytic corrosion under powered moisture conditions; and

the outer moisture barrier formed from deposition of tantalum oxide on the nickel-chromium alloy thin film layer and not through oxidation of tantalum.

Claim 14 (Canceled).

Claim 15 (Previously presented): A nickel-chromium alloy thin film chip resistor resistant to moisture without use of metallic tantalum comprising:

an alumina substrate;

REST AVAILABLE COPY

a single nickel-chromium alloy thin film layer directly contacting the substrate;

a non-tantalum chip resistor termination attached on each end of the nickel-chromium alloy thin film:

a passivation layer directly overlaying and contacting the nickel-chromium alloy layer;

an outer moisture barrier consisting of tantalum pentoxide directly overlaying and contacting the

passivation layer for reducing failures due to electrolytic corrosion under powered

moisture conditions; and

the outer moisture barrier formed from deposition of tantalum oxide on the passivation layer and not through oxidation of tantalum.

Claim 16 (Canceled).

Claim 17 (Currently amended): A thin film chip resistor resistant to failures due to electrolytic corrosion under powered moisture conditions without use of a tantalum nitride system and without use of a screen-printed moisture barrier, comprising: a substrate;

a single thin film resistive element overlaid on the substrate;

a chip resistor termination attached on each end of the thin film resistive element; and an outer moisture barrier consisting of tantalum pentoxide directly overlaying and contacting the thin film resistive element to reduce failures due to electrolytic corrosion under powered moisture conditions.

REST AVAILARIE COPY

Claim 18 (Previously presented): The thin film chip resistor of claim 17 wherein the outer moisture barrier prevents failure after MIL-STD-202 testing.

Claim 19 (Previously presented): The thin film chip resistor of claim 17 wherein the chip resistor termination is wrap around termination.

Claim 20 (Previously presented): The thin film chip resistor of claim 17 wherein the thin film resistive element is a metal thin film resistive element.

BEST AVAILABLE COPY